

Laguna Clay Co. Moist Clays

1230 E. Mermaid Lane
Wyndmoor, PA 19038

10 White Clay



Cone 06-04

A smooth, plastic, talc free white firing clay, suitable for throwing and sculpture. Ideal for beginners and schools. Most low-fire commercial glazes fit this body when bisque fired to Cone 04. Shrinkage @ c/05 - 8.0%, Absorption @ c/05 - 11.5%

10-G White Clay w/Grog



Cone 06-04

This clay has the same properties as # 10, but with medium grog added for larger thrown and sculpture pieces. Lower shrinkage. Shrinkage @ c/05 - 7.8%, Absorption @ c/05 - 11.5%

12 Buff Clay



Cone 06-04

A low fire plastic talc body. Fires buff in color. Very good for both handbuilding and throwing. Popular with teachers and schools Shrinkage @ c/05 - 7.%, Absorption @ c/05 - 12%

15 Porcelain Clay



Cone 6

Translucent porcelain. An excellent grogged body for throwing thin pieces- large or small. Shrinkage @ c/6 - 14.9%, Absorption @ c/6 - 0.09%

20 Red Clay



Cone 06-04

A smooth, plastic, terra cotta colored clay for wheel throwing and excellent for hand building as well. Fires to a rich terra cotta red. Shrinkage @ c/05 - 8.5%, Absorption @ c/05 - 11.0%

20-G Red Clay w/grog



Cone 06-04

This clay has the same properties as # 20 with a fine grog added for slightly less shrinkage and improved workability. Shrinkage @ c/05 - 8.0%, Absorption @ c/05 - 11.5%

40 Buff Clay



Cone 6

A dark buff firing clay. Versatile, medium textured throwing body. Shrinkage @ c/6 - 11.9%, Absorption @ c/6 - 2.87%

55 Clay



Cone 6

Excellent off-white stoneware clay for wheel work. Minor specking caused by fireclay enhances appearance. Used by many for functional pottery. Shrinkage @ c/6 - 11.9%, Absorption @ c/6 - 2.87%

66 Clay



Cone 6

White stoneware includes sand, making it quite desirable for tile, slabs and handbuilding. Shrinkage @ c/6 - 12.5%, Absorption @ c/6 - 1.5%

To Place an order call 215-233-0655 or fax 215-233-0496



1230 E. Mermaid Lane
Wyndmoor, PA 19038

Laguna Clay Co. Moist Clays

#70 Clay



Cone 6

A plastic throwing clay, dark in color, featuring heavy specking. Creates excellent glaze effects with dark gray color and specks Shrinkage @ c/6 - 12.5%, Absorption @ c/6 - 1.35%

#90 Clay



Cone 6

Formulated with fine grog and red art to obtain rich dark color. Good for outdoor pots as well as functional pottery and sculpture, when fired to cone 6. Shrinkage @ c/6 - 13%, Absorption @ c/6 - 0.9%

200 Clay



A heavily grogged raku clay formulated to resist thermal shock. no information on shrinkage or absorption available.

403 Speckled Buff Clay



Cone 5

This clay is smooth textured and an excellent throwing body. Fired in Oxidation, speckled buff falls into the tan/brown color range. Low in grog and sand content. Shrinkage @ c/5 - 12%, Absorption @ c/6 - 3%

510 White Stoneware



Cone 10

A very popular white stoneware. This clay is a plastic, smooth throwing clay with superior handbuilding and slab properties. Contains fine grog. Shrinkage @ c/10 - 13%, Absorption @ c/10 - 1%

550 Porcelain Clay



Cone 10

This porcelain is made primarily of English Grolleg. It contains plasticizers to make this the finest translucent porcelain available for throwing, thin slab work and handbuilding. Shrinkage @ c/10 - 14.7%, Absorption @ c/10 - 0.3%.

750 Brown Stoneware



Cone 10

Tan in oxidation and a darker toast in reduction. This clay is excellent for wheel, slab and sculpture. Excellent body color and good texture. Do not over reduce as it goes too dark. Shrinkage @ c/10 - 14.5%, Absorption @ c/10 - 0.7%

850 Cream Stoneware



Cone 10

An off-white, typical light stoneware throwing clay. Medium texture for good tooth. Contains fireclay, no additional color. Shrinkage c/10 - 14.5%, Absorption @ c/0.31

To Place an order call 215-233-0655 or fax 215-233-0496



Laguna Clay Co. Moist Clays

1230 E. Mermaid Lane
Wyndmoor, PA 19038

910 Stoneware Clay



Cone 10

This low sulfur body is less prone to bloating than most clays in cone 10 reduction firings. You will appreciate minimal sulfur odor. Warm toast color in reduction. Shrinkage @ c/10 - 12.7%, Absorption @ c/10 - 0.6%

B3 Dark Brown Clay



Cone 5

A pliable clay with smooth grog and color from manganese and iron. Fires almost black when reduced and dark brown/black in oxidation. Shrinkage @ c/5 10%, Absorption @ c/5 - 3%

B-Mix 5 Clay



Cone 5

This clay offers the same characteristics as B Mix 10. It's smooth porcelain like texture is a pleasure to throw and form and it fires to a cream color in oxidation. Shrinkage @ c/6 - 12%, Absorption @ c/6 - 2.75%

B-Mix 10 Clay



Cone 10

A premier, cream-white, throwing clay that is easy to throw and form. Smooth porcelain texture. Fires Gray/white in reduction and lighter in oxidation., Shrinkage @ c/6 - 13%, Absorption @ c/6 - 1.0%

Red B-Mix with Grog



Cone 5

A medium sized grog version of our popular Cone 5 B Mix clay body with the addition of Red clay to achieve a warm Orange Brown color. Very forgiving during drying and good for forming larger sized objects. Shrinkage @ c/5 - 9%, Absorption @ c/5 - 4%

Party Clay

Low Fire Only

An economy clay good for making molds, low fire or unfired purposes. It is made of a variety of clays and can only be low fired. The color and consistency varies from batch to batch. Not suitable for production. Because of the variety of the product, no shrinkage or absorption information is available.



1230 E. Mermaid Lane
Wyndmoor, PA 19038

Laguna Clay Co. Moist Clays

Clay	50 lb per lb	100 lb per lb	500 lb per lb	1000 lb per lb	2000 lb per lb
10	.46	.42	.38	.35	.33
10G	.47	.43	.39	.36	.33
12	.51	.46	.42	.39	.36
15	.84	.76	.69	.63	.59
20	.55	.49	.45	.41	.38
20G	.57	.51	.47	.43	.40
40	.51	.46	.42	.38	.36
55	.50	.45	.41	.38	.35
66	.53	.48	.44	.40	.37
70	.55	.50	.45	.42	.39
90	.55	.50	.45	.42	.39
200	.55	.50	.45	.42	.39
403	.64	.58	.53	.49	.45
510	.57	.52	.47	.42	.40
550	.97	.88	.80	.74	.68
750	.57	.51	.47	.43	.40
850	.52	.47	.43	.40	.37
910	.54	.49	.44	.41	.38
B3	.66	.60	.54	.50	.46
B-Mix 5	.50	.45	.41	.38	.35
B-Mix 10	.51	.46	.42	.39	.36
Red B-Mix 5 w/grog	.66	.60	.54	.50	.46
Party Clay	.32	.30	.27	.25	.23

Laguna Clay Co. Liquid Casting Slip

all slip packed in 2-1/2 gallon plastic bag inside a carton

Miller Slip



Cone: 06/04

Avg. Shrinkage 2±% 4.5%

Avg. Water Absorption 1±% 15.2%

Robbins Red Slip



Cone: 06/04

Avg. Shrinkage 2±% 11.8%

Avg. Water Absorption 1±% 2.5%

Dover Slip



Cone: 6

Avg. Shrinkage 2±% 11.6%

Avg. Water Absorption 1±% 0.0%

Laguna Miller Liquid Casting Slip	price per box
Miller Slip	12.00
Robbins Red Slip	16.00
Dover Slip	13.50